



TEST REPORT

DATE: 03-18-2016

TEST NUMBER: 0226749

CLIENT	Egetaepper a/s
---------------	----------------

TEST METHOD CONDUCTED	AATCC 164 Colorfastness to Oxides of Nitrogen in the Atmosphere under High Humidities
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Una Temp ECT350
CONSTRUCTION	Loop Pile
BACKING	Attached Cushion

GENERAL PRINCIPLE

Test specimens are subjected to oxides of nitrogen in a test chamber at elevated temperatures with the relative humidity above 85%. After a predetermined number of exposure cycles the test specimens are examined for color change and rated in accordance with the AATCC Gray Scale for Evaluating Color Change.

TEST RESULTS

EXPOSURE	2 Cycles
-----------------	----------

COLOR	RATING
Una Temp ECT350	5.0

COLOR	RATING

COLOR	RATING

AATCC RATING KEY	
5	No change
4	Slight change
3	Noticeable change
2	Considerable change
1	Severe change

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.