

Impact sound reduction according to ISO 140-8

Measurement of the impact sound reduction through a ceiling pad on a solid reference ceiling in test stands

On behalf of: EGETÆPPER A/S, INDUSTRIVEJ NORD 25, DK-7400 HERNING

Object:

Una Level WT

Assembly:

ITEM: 0915330

BATCH: TH07265-0024

BALE: 357049960108487827



Volume of the receiving room: 53,3 m³

Temperature: 20,9 °C


Test stand: ARL

Humidity: 43,7 %

Day of measurement: 07.11.2024

Air pressure: 97,5 kPa

Frequency f [Hz]	L _{n,0} Third [dB]	ΔL Third [dB]
50	66,9	4
63	57,5	0,8
80	60,1	4,9
100	58,7	0
125	65,4	-0,8
160	72,5	1,4
200	73,1	1,8
250	68,0	1,7
315	69,4	2,4
400	69,3	2,9
500	70,2	4,6
630	71,3	5
800	71,7	6,7
1000	72,8	9,2
1250	74,1	12,4
1600	75,4	16,8
2000	73,7	22,4
2500	72,3	29,9
3150	72,5	38,5
4000	71,3	44,4
5000	69,2	49



Parameters according DIN EN ISO 717-2:

$\Delta L_w = 14$ dB

$C_{l,\Delta} = -9$ dB

$C_{l,r} = -2$ dB

The measurement results are based on tests carried out with an artificial sound source.

Measurements in third octave band width.

Akustik Raum Labor

Wächtersbach,

20.12.2024

Signature:

Report-No.: ARL202411070

Test-No.: M05

Akustik Raum Labor A.R.L. GmbH
Industriestr. 38
63607 Wächtersbach

☎ + 49 (0) 6053 62067 0

☎ + 49 (0) 6053 62067 26

✉ info@akustik-raum-labor.de