

## **TEST REPORT**

DATE: 08-24-2017	Page 1 of 1	TEST NUMBER:	0240040
CLIENT	Egetaepper a/s		
TEST METHOD CONDUCTED	ASTM D5252 Standard Practice for Hexapod Tumble Drum Tester	the Operation	of the

DESCRIPTION OF TEST SAMPLE			
IDENTIFICATION	Highline 80/20 1400 ECT350		
CONSTRUCTION	Cut Pile		
BACKING	Attached Cushion		
REFERENCE	Modular Collection		

## **GENERAL PRINCIPLE**

The test specimen is subjected to "Hexapod" tumbling in 2,000 cycle increments. A CRI/SOA upright vacuum was used to make four forward and backward passes along the length of the specimen after each 2,000 cycles.

After the specified total number of cycles is completed, the test specimen is visually assessed by three technicians for appearance change in accordance with the ASTM D7330 "Test Method for Assessment of Surface Appearance Change in Pile Floor Coverings Using Standard Reference Scales".

## **TEST RESULTS**

## **LIGHT BALL**

NUMBER OF CYCLES	APPEARANCE RATING	COLOR CHANGE RATING*
12,000	4.0	2.0

\*NOTE: At the client's request, an additional rating was reported which assessed perceived color change in the test specimen resulting from pile distortion. The color change rating was done in accordance with AATCC Evaluation Procedure 1, using the Gray Scale for Color Change.

APPEARANCE RATING KEY			COLOR CHANGE RATING KEY	
5	Excellent: No visual change noticeable		5 Negligible or no change	
4 Good: Slight change due to disturbance of pile			4 Slight change	
<b>3</b> Fair: Noticeable change due to pile disturbance or matting			3 Moderate change	
<b>2</b> Poor: Loss of texture due to pile disturbance and/or matting			2 Considerable change	
1	Very Poor: Severe pile disturbance and/or matting 1 Severe change		1 Severe change	
APPROVED BY: Harry atluny			qalv <sub>i</sub> n	

This facility is accredited by the National Voluntary Laboratory Program for the specific scope of accreditation under lab code 100297-0. This accreditation does not constitute endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place

Phone: 706-226-3283

email: protest@optlink.us

Fax: 706-226-6787



APPROVED BY:

Lary athury

NVLAP LAB CODE 100297-0

Fax: 706-226-6787

This facility is accredited by the National Voluntary Laboratory Program for the specific scope of accreditation under lab code 100297-0. This accreditation does not constitute endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place

Dalton, GA 30721

Phone: 706-226-3283

email: protest@optlink.us